



# 9485 & 926 Transfer Tapes

## Product Data Sheet

Updated : February 1996  
Supersedes : October 1993

<b>Product Description</b>	<b>9485 Transfer Tape</b>	A-25 is a firm acrylic pressure-sensitive adhesive system. It features very high adhesion to a variety of surfaces, excellent shear holding power, high temperature resistance and an excellent UV resistance.
	<b>926 Reverse Wound Transfer Tape</b> for use with 3M 'ATG' Tape Dispensers.	

### Physical Properties

Not for specification purposes

<b>Adhesive Type</b>	Firm Acrylic	<b>3M ref</b> : A-25
<b>Thickness</b> (ASTM D-3652) Tape Liner Total	130 µm      5 Thou 100 µm 230 µm	
<b>Release Liner</b>	Moisture Resistant Tan Paper / Tan Paper (926)	
<b>Tape Colour</b>	Clear	
<b>Shelf Life</b>	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

### Performance Characteristics

Not for specification purposes

<b>Adhesion to Stainless Steel</b> ASTM D-3330	16.3 N/10mm	See Peel Adhesion continued below.
<b>Shear Resistance</b>	Excellent.	See static Shear Adhesion continued below.
<b>Temperature Performance</b> Max : Minutes / Hours Max : Days / Weeks Minimum	230 °C 150 °C - 30 °C	
<b>Solvent Resistance</b>	Very Good.	
<b>UV Light Resistance</b>	Excellent.	

Date : February 1996  
9485 & 926 Transfer Tapes

---

### Additional Product Information

9485 has a moisture resistant liner which can withstand high humidity conditions with minimal cockling or wrinkling.

926 is used in the ATG hand dispensers.

---

### Application Techniques

1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength.

2. To obtain optimum adhesion, the bonding

surfaces must be clean dry and well unified. A typical surface cleaning solvent is isopropyl alcohol. Use proper safety precautions for handling solvents.

3. Ideal tape application temperature range is 21°C to 38°C (70°F to 100°F).

Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended because the adhesive becomes too firm to adhere readily. However once properly applied low temperature holding is generally satisfactory.

---

### Applications

These tapes are well suited for joining a wide variety of similar and dissimilar materials where high temperature performance and excellent UV resistance is required.

Trim, stiffener and fascia bonding.

High stress splicing e.g. Wallpaper, Metals.

---

### PEEL ADHESION (ASTM D-3330)

(180° peel, room temperature conditions)

### SURFACE

Stainless Steel  
Aluminium  
Painted Metal  
Glass  
Polycarbonate  
Acrylic  
Epoxy  
ABS  
Rigid PVC  
Polypropylene  
L.D. Polyethylene  
H.D. Polyethylene

### 15 min dwell N/10mm

11.4  
4.9  
7.6  
13.1  
12.5  
10.9  
9.3  
7.6  
5.5  
5.5  
3.8  
3.3

### 72 hr dwell N/10mm

16.4  
10.4  
15.8  
15.8  
14.7  
13.6  
13.1  
9.3  
9.8  
6.5  
4.4  
3.8

Date : February 1996  
9485 & 926 Transfer Tapes

<u>Static Shear Adhesion</u> <u>(ASTM D-3654)</u> (1sq. in. Area contact - aluminium to stainless steel - 72hr dwell)	<u>Temperature</u> °C	<u>Load</u> g	<u>Minutes to Failure</u>
	20	1000	NO FAILURES - TESTS DISCONTINUED AFTER 10,000 min.
	70	400	
	90	400	
	120	300	
	150	300	
	175	300	
	230	200	

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



### Specialty Tapes & Adhesives

© 3M United Kingdom PLC 1996

3M United Kingdom PLC  
3M House,  
28 Great Jackson Street,  
Manchester,  
M15 4PA

Customer Service :  
Tel 0161 236 8500  
Fax 0161 237 1105

3M Ireland  
3M House, Adelphi Centre,  
Upper Georges Street,  
Dun Laoghaire, Co. Dublin,  
Ireland

Customer Service :  
Tel (01) 280 3555  
Fax (01) 280 3509